




**Part Number:** **MS-134075-2**

Revision 2021-Dec-01 - Generated 2021-Dec-01



(If coated, Max./Min. includes coating)

<b>OD</b>	(nom. - bare core) (max.)	33.02 mm 33.83 mm	1.300 in 1.332 in										
<b>ID</b>	(nom. - bare core) (min.)	19.94 mm 19.30 mm	0.785 in 0.760 in										
<b>HT</b>	(nom. - bare core) (max.)	18.00 mm 19.00 mm	0.709 in 0.748 in										
<b>Mass</b>	(approximate)	53 grams											
<b>Magnetic Dimensions</b>	A <sub>e</sub> - Eff. Mag. Cross Section	1.10 cm <sup>2</sup>											
	L <sub>e</sub> - Eff. Mag. Path Length	8.15 cm											
	V <sub>e</sub> - Eff. Core Volume	8.98 cm <sup>3</sup>											
	WA - Min. Eff. Window Area	2.93 cm <sup>2</sup>											
	sa - Surface Area	49.1 cm <sup>2</sup>											
<b>Inductance</b>	μ <sub>i</sub> (reference)	75											
	A <sub>L</sub> value (nominal)	127.5 nH/N <sup>2</sup>											
	Test Winding	N=70, #22 AWG											
	Frequency	10 kHz											
	Voltage on Agilent 4284A	0.34 V											
<b>Core Loss</b>	AL tolerance	±8%											
	$\text{Core Loss (mW/cm}^3\text{)} = \frac{a}{B_{pk}^3} + \frac{b}{B_{pk}^{2.3}} + \frac{c}{B_{pk}^{1.65}} + d \cdot B_{pk}^2 \cdot f^2$												
	where B <sub>pk</sub> expressed in gauss, f expressed in hertz, and: a=7.890E+09, b=7.111E+08, c=8.980E+06, d=2.846E-14												
	B <sub>pk</sub>	1000 G											
	frequency	50 kHz											
<b>DC Saturation</b>	Core Loss (nominal)	323 mW/cm <sup>3</sup>											
	Core Loss (maximum)	372 mW/cm <sup>3</sup>											
	$\% \mu_i = \frac{1}{a + b \cdot H^c} + d$												
	where H expressed in oersteds, and: a=1.000E-02, b=3.414E-06, c=1.841, d=0.000												
	H <sub>dc</sub>	80 Oe											
<b>Coating/Pkg</b>	Percent Initial Perm(nom.)	47.9%											
	Percent Initial Perm(min.)	39.6%											
	Coating Type:	Blue Epoxy											
	Voltage Breakdown (min.)	1000 Vrms											
<b>Winding Table</b>	Limit	0.1 mA, 5 s											
	Package Quantity	320 Pcs/Box											
	<b>Wire Size</b>	AWG	8	10	12	14	16	18	20	22	24	26	28
		mm	3.150	2.500	2.000	1.600	1.250	1.000	0.800	0.630	0.500	0.400	0.315
	<b>Single Layer</b>	Turns	14	18	22	29	36	46	58	73	91	114	142
Rdc(Ω)		1.8 m	3.7 m	7.1 m	14.9 m	29.4 m	59.8 m	120.0 m	240.2 m	476.2 m	948.7 m	1.9	
<b>Full Winding</b>	Turns	15	24	37	57	88	136	211	326	504	780	1,208	
	Rdc(Ω)	1.9 m	4.9 m	12.0 m	29.3 m	72.0 m	176.9 m	436.5 m	1.1	2.6	6.5	16.0	

